

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number  
WO 2004/011517 A1

(51) International Patent Classification<sup>7</sup>: C08F 297/08,  
C08L 23/08

(74) Agent: FRANK B. DEHN & CO., 179 Queen Victoria  
Street, London EC4V 4EL (GB).

(21) International Application Number:  
PCT/GB2003/003217

(22) International Filing Date: 29 July 2003 (29.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 29 July 2002 (29.07.2002) GB  
0217520.6

(71) Applicant (for all designated States except US): BORE-  
ALIS TECHNOLOGY OY [FI/FI]; P.O. Box 330, FIN-  
06101 Porvoo (FI).

(71) Applicant (for GB only): CAMPBELL, Neil [GB/GB];  
179 Queen Victoria Street, London EC4V 4EL (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): MYHRE, Ole, Jan  
[NO/NO]; Borealis AS, N-3960 Stathelle (NO). SKAR,  
Merete [NO/NO]; Lærer Johnsenvei 2, N-3960 Stathelle  
(NO). DAVIKNES, Hans, Georg [NO/NO]; Tryms vei  
8, Stathelle (NO). BROVE, Kjetil, Larsen [NO/NO];  
Kalliasen 23, Stathelle (NO). JOHANSEN, Geir, Morten  
[NO/NO]; Borealis AS, N-3960 Stathelle (NO).

(81) Designated States (national): AE, AG, AL, AM, AT (util-  
ity model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA,  
CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (util-  
ity model), DE, DK (utility model), DK, DM, DZ, EC, EE  
(utility model), EE, ES, FI (utility model), FI, GB, GD, GE,  
GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ,  
LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,  
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO,  
RU, SC, SD, SE, SG, SK (utility model), SK, SL, SY, TJ,  
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA,  
ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: SHRINK FILM

(57) Abstract: A shrink film comprising a polyethylene film, characterized in that said polyethylene is an ethylene copolymer mix-  
ture having a molecular weight distribution in the range 10 to 35, a density of 915 to 940 kg/m<sup>3</sup>, a weight average molecular weight  
of at least 100000 D and an MFR<sub>2.16</sub> (190 °C) of 0.1 to 0.9 kg/m<sup>3</sup>, which copolymer mixture is produced by a two or more stage  
copolymerization of ethylene and 2 to 10 % mole (relative to ethylene) of a C<sub>3-12</sub> alpha-olefin comonomer in a series of reactors  
including at least one slurry loop reactor and at least one gas phase reactor using a heterogeneous Ziegler-Natta catalyst.

WO 2004/011517 A1